

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C02F 3/10, C12N 11/00	A1	(11) International Publication Number: WO 99/40035 (43) International Publication Date: 12 August 1999 (12.08.99)
(21) International Application Number: PCT/GB99/00346 (22) International Filing Date: 2 February 1999 (02.02.99) (30) Priority Data: 9802388.0 4 February 1998 (04.02.98) GB (71)(72) Applicant and Inventor: TODD, John, James [GB/GB]; 17 Maltings Close, Alton, Hampshire GU34 1DT (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): HOPWOOD, Adrian [GB/GB]; Glebe House, High Street, Childrey, Wantage, Oxfordshire OX12 9UP (GB). (74) Agents: BEN-NATHAN, Laurence, Albert et al.; Urquhart-Dykes & Lord, 91 Wimpole Street, Lon- don W1M 8AH (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: WASTE WATER TREATMENT, MEDIA THEREFOR AND ITS MANUFACTURE (57) Abstract A loose particulate material for use in waste water treatment comprises granules of plastics material carrying weighting material so that the granules have an average density of approximately 1.0 g/cc. At least a portion of the weighting material is carried within the granules and the surfaces of the granules are provided with concavities to provide a habitat for organisms effective in waste water treatment. The particles are manufactured by incorporating a weighting material into the granules, contacting the granules with grains of a soluble substance of an elevated temperature to coat the granules with the soluble substance grains and subsequently dissolving the soluble substance grains.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakistan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Waste Water Treatment, Media Therefor and Its Manufacture

This invention relates to loose particulate material for use in waste water treatment plant and methods, to the manufacture of such material, and to methods and apparatus for the treatment of waste water using such material.

Waste water may be treated by gasification, for example by the aeration or oxygenation of sewage or other waste water containing organic matter degradable by the action of oxygen thereon. A wide range of treatment methods and apparatus has been used and proposed. Oxygen does not dissolve easily or quickly in water and it is therefore in principle desirable to utilize fine bubble aerators wherein the bubbles are less than 2 mm and desirably less than 1 mm in diameter. Smaller bubbles have a larger specific surface area for oxygen transfer into the liquid, and also rise more slowly through the liquid to give a longer time for the oxygen to transfer before the bubble reaches the liquids surface. Treatment plants are known comprising a treatment vessel with aerator devices submerged in the waste water to produce the bubbles.

It has also been proposed to provide a treatment plant where the treatment vessel contains a bed of loose material. Aeration then causes a degree of fluidization of the bed and sustains the growth of a population of microorganisms on the material of the bed. In the presence of dissolved oxygen the microorganisms convert the organic matter in the waste water to carbon dioxide, water and to more bulky cellular materials and sludge thus alleviating the biological oxygen demand (BOD). Under appropriate operating conditions they will also convert ammonia to nitrate compounds. The surplus sludge

thus formed can pass out with the effluent for eventual separation and recycling if desired.

Problems of fouling and clogging of the aerator devices and any pipe work can be acute where they are buried or caged beneath a bed of loose material. Regular closing and draining of the plant for cleaning and unblocking or replacement of the aerators is inefficient and expensive due to the need also to move aside or remove the filter bed material to gain access to the buried aerators.

Our publication no. WO/95/17351 describes a method and apparatus for treatment of waste water wherein such problems are mitigated, and in particular discloses loose particulate material for use as a fluidizable bed in the waste water treatment, said material being characterized by particles of a substantially inert mineral adhered to, coated on or coated by plastics material to provide a habitat for microorganisms effective in waste water treatment.

That Publication discloses such loose particulate material having a density in the range of from substantially 1.0 to substantially 1.3 g/cc, having a specific surface area in excess of approximately 600 m² per cubic metre of the loose material, and having a particle size range of substantially 3 mm to substantially 10 mm in diameter. An example of the material is disclosed as particles of sand or other inert mineral particles at least partially adhered to, coated on or coated by plastics material, preferably a thermoplastics material such as polyethylene. It was disclosed that the material could be produced to a desired density for a particular application by changing the initial proportions of mineral and plastics.

Our Publication No. WO/96/25367 describes improved loose particulate material for use in waste water treatment. It

discloses granules of plastics material having grains of an inert mineral such as sand coated thereon, the granules having a predetermined particle size range, and the grains having a predetermined particle size range and being disposed at a predetermined packing density range on the granules. The particles have an average density of approximately 1.0 g/cc such that a proportion tends to float and a proportion tends to sink in the waste water. The particles are manufactured by contacting the granules of plastics material with a mixture of grains of the inert mineral and grains of a soluble substance such as salt, at an elevated temperature, to coat the granules with the mixture, and subsequently dissolving the soluble substance grains from the coating to provide the granules coated with the grains of inert mineral in the predetermined packing density range.

Such loose particulate material has been found in practice to be effective for use in waste water treatment. Such materials have been found to provide a particularly suitable habitat for a high population density of microorganisms of the type effective in waste water treatment.

The inventors have also found that, by using significantly embedded grains, the subsequent step of dissolving away the soluble substance grains leaves concavities in the surface of the granules thereby aiding achievement of the desired high specific surface area.

An object of the present invention is to provide further improved material for waste water treatment and methods for its manufacture.

According to the present invention in one aspect there is provided loose particulate material for use in waste water treatment, said material characterised by granules of plastics material carrying weighting material so that the

particles have an average density of approximately 1.0 g/cc, at least a proportion of said weighting material being carried within the granules, and the surface of the granules being provided with concavities to provide a habitat for microorganisms effective in waste water treatment.

The weighting material, i.e. filler, may be grains of sand, salt, lime, chalk or other substantially inert mineral.

The weighting material is preferably incorporated substantially wholly within the granules such that the weighting material is substantially not exposed at the surface of the granules.

An advantage of incorporating the grains of weighting material largely or wholly within the granules is that the grains can achieve the required weighting function to bring the average particle density to approximately 1.0 g/cc and reducing their likelihood of becoming gradually abraded away over an extended period of use. It is desirable for waste water treatment plants to function for periods of many years between major refits.

If the sand grains are largely exposed on the surface of the granules, as with the particles described in our above-mentioned WO/96/25367, they may become abraded away over a period of use. The proportion of granules of lower density than aerated waste water would then be undesirably increased.

However, the invention includes particles wherein the granules have both weighting material incorporated wholly within the granules and also a surface coating of grains. The weighting material and the surface grains may both be grains of sand or other substantially inert mineral. The surface grains provide convexities thus cooperating with the concavities to increase the specific surface area and thus to increase the habitat area for the microorganisms. A further

advantage of providing some surface grains is that they can effectively prevent the granules from adhering to one another, during manufacture or use, in undesirable agglomerations.

The present invention also provides a method of manufacture of loose particulate material for use in waste water treatment, said method comprising incorporating a weighting material within granules of plastics material so that at least a proportion of the weighting material is carried within the granules and the particles have an average density of approximately 1.0 g/cc, and contacting the granules with grains of a soluble substance, at an elevated temperature, to coat the granules with the soluble substance grains, and subsequently dissolving the soluble substance grains from the coating to provide the surface of the granules with concavities to serve as a habitat for microorganisms effective in waste water treatment.

The grains of a soluble substance can conveniently be salt grains.

The granules are preferably contacted with the soluble substance grains at an elevated temperature such that the grains coat the granules by burying themselves significantly into a partially melted outer surface of the granules, whereby the step of dissolving the soluble substance grains leaves the desired concavities in the granules surface.

In another aspect the present invention provides a waste water treatment medium characterised by a plastics material substrate having a surface provided with concavities to provide a habitat for microorganisms effective in waste water treatment.

The medium may be a structure adapted to be fixed in position within a waste water treatment vessel.

In yet a further aspect, the present invention provides a method of manufacture of a waste water treatment medium comprising contacting a plastics material substrate with grains of a soluble substance, at an elevated temperature, to coat the substrate with the soluble substance grains, and subsequently dissolving the soluble substance grains from the coating to provide the surface of the substrate with concavities to serve as a habitat for microorganisms effective in waste water treatment.

An embodiment of the invention will now be described.

Granules of plastics material are provided. These are suitably granules of polyethylene and preferably have substantially uniform particle size. The particle size is suitably in the range 3 to 10 mm considered as a sieve size range. The preferred size range is 4 to 8 mm, preferably about 6 mm. The granules may be of approximately spherical, ellipsoidal or cylindrical shape, or may be of irregular shape such as commercially available recycled chips, for example granulated from moulded rejects. Flattened shapes have a greater specific surface area.

It is desired to achieve a high specific surface area for the loose particulate material, for example in excess of about 600 m² per cubic metre or even 2000 m² per cubic metre. The greater the specific surface area, the correspondingly larger is the habitat area for the microorganisms effective in the treatment.

The specific gravity of the plastics material is fixed by the choice of plastics material, suitably polyethylene, and is less than 1.0 g/cc. The granules carry weighting materials so that the particles have an average density of approximately 1.0 g/cc. Thus in use a proportion of particles tend to float and a proportion tend to sink in the

waste water, but on average have neutral buoyancy so as to circulate easily as the waste water is aerated and circulated. The density is preferably a little less than 1.0 g/cc because aerated waste water itself has a density a little less than 1.0 g/cc.

The weighting material is suitably grains of sand and is preferably incorporated substantially wholly within the granules. However the invention includes embodiments wherein the granules have sand grains incorporated wholly within the granules and also a surface coating of sand grains. The specific gravity of the mineral, e.g. sharp sand, is substantially greater than 1.0 g/cc and thus the relative quantity of said grains to be incorporated in the granules is determined by the specific gravity of the plastics material to bring the resultant particles up to the desired density of approximately 1.0 g/cc.

The surface of the weighted granules is provided with concavities to serve as habitats for microorganisms effective in waste water treatment. The concavities preferably cover substantially the whole surface of the granules, thereby providing the greatest possible increase in effective surface area.

The concavities may be about 0.1 mm to 1 mm in effective width and in effective depth, preferably about 0.3 mm in width and a little less in depth. It will be appreciated that if such concavities cover substantially the whole surface of the granules then the specific surface area is increased by a factor of about 3 or more, also depending upon the general shape and regularity of the concavities themselves.

The concavities not only increase the specific surface area, and thus the available habitat area for the

microorganisms, but they also provide a sheltered environment which particularly favours the growth of a desirably dense and stable population of microorganisms. In prior art arrangements with microorganisms exposed on the external surfaces of media or structures, they are liable to become detached by abrasion or tumbling during circulation of waste water.

A particular advantage of the particles of the present invention is that they are loose and of neutral buoyancy, and are thus continually mobile within and throughout the body of waste water within the treatment vessel. Thus, during circulation and aeration this ensures high efficiency of contact between the microorganisms and the waste water being treated.

However, an advantage of the invention can also be achieved in relation to other waste water treatment media, for example structures adapted to be fixed in position within a waste water treatment vessel. Such medium is also preferably a plastics material and has a surface similarly provided with said concavities to provide a habitat for microorganisms effective in waste water treatment.

The loose particulate material is suitably manufactured by incorporating the weighting material within the plastics material granules and then creating the surface concavities. The weighted granules are contacted with grains of a soluble substance, at an elevated temperature, to coat the weighted granules with the soluble substance grains, and subsequently dissolving the soluble substance grains from the coating to provide the surface of the granules with the concavities.

The soluble substance may be common salt, i.e. sodium chloride. The salt grain size range is of course governed by the desired size of the eventual concavities and is suitably

about 0.3 mm. Salt grains tend to be cubic crystals and thus the eventual concavities also tend to be generally cubic. This is advantageous in increasing the specific surface area.

The soluble substance may however be any economically available granular substance which is soluble in a common solvent, such as water, that does not affect the plastics material and provided that it has a melting point higher than the softening point of the polyethylene granules, i.e. higher than about 200°C.

The weighting material may be identical to the soluble substance. For example, both may be common salt grains. The salt grains incorporated within the granules as weighting material would thereby tend to be protected from being dissolved away by the waste water.

It has been found possible to provide loose particulate material having a specific surface area considerably in excess of 600 m² per cubic metre, i.e. up to 3000 m² per cubic metre or 4000 m² per cubic metre. Moreover, the concavities provide a sheltered environment which particularly favours the growth of a desirably dense and stable population of microorganisms. The material finds use in waste water treatment plants and methods for example as described in our above-mentioned WO/95/17351 or WO/96/25367.

Claims

1. Loose particulate material for use in waste water treatment, said material characterised by granules of plastics material carrying weighting material so that the particles have an average density of approximately 1.0g/cc, at least a proportion of said weighting material being carried within the granules, and the surfaces of the granules being provided with concavities to provide a habitat for microorganisms effective in waste water treatment.
2. Loose particulate material according to claim 1, in which the weighting material is incorporated substantially wholly within the granules such that the weighting material is substantially not exposed at the surfaces of the granules.
3. Loose particulate material according to claim 1 or claim 2 in which the weighting material is salt grains.
4. Loose particulate material according to claim 1, in which the weighting material is incorporated within the granules and adhered to the surfaces of the granules.
5. Loose particulate material according to claim 1 or claim 4, in which the weighting material is sand grains.
6. Loose particulate material according to any preceding claim, in which the weighting material is a mixture of sand and salt grains.

7. A method of manufacture of loose particulate material for use in waste water treatment, said method comprising incorporating a weighting material within granules of plastics material so that at least a proportion of the weighting material is carried within the granules and the particles have an average density of approximately 1.0g/cc, and contacting the granules with grains of a soluble substance, at an elevated temperature, to coat the granules with the soluble substance grains, and subsequently dissolving the soluble substance grains from the coating to provide the surfaces of the granules with concavities to serve as a habitat for microorganisms effective in waste water treatment.

8. A method according to claim 7, in which the soluble substance grains are salt grains.

9. A waste water treatment method characterised by charging a treatment vessel with waste water and loose particulate material according to any one of claims 1 to 6, and aerating the waste water by means of aerators.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 99/00346

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C02F3/10 C12N11/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C02F C12N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 96 25367 A (PROCEFF LTD ;TODD JOHN JAMES (GB); HOPWOOD ADRIAN (GB)) 22 August 1996 cited in the application see the whole document	1,4,5, 7-9
A	---	6
Y	WO 95 17357 A (DOW CHEMICAL CO) 29 June 1995 cited in the application ESPECIALLY FROM PAGE 4, LINE 26 TO PAGE 5, LINE 5	1,2,4,5, 9
Y	WO 86 05811 A (VERAX CORP) 9 October 1986 see page 10, line 9 - page 11, line 16 --- -/--	1,2

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

25 May 1999

Date of mailing of the international search report

04/06/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040. Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Devisme, F

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 99/00346

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4 915 884 A (CAPDEVILLE BERNARD ET AL) 10 April 1990 see the whole document -----	1-3, 7-9
Y	US 4 576 718 A (A. REISCHL ET AL) 18 March 1986 see column 5, line 29 - column 6, line 29 -----	1, 3, 5

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 99/00346

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9625367	A	22-08-1996	AU 4671396 A	04-09-1996
			CA 2211649 A	22-08-1996
			EP 0871595 A	21-10-1998
			FI 973133 A	08-10-1997
			HU 9801413 A	28-09-1998
			NO 973712 A	19-09-1997
			NZ 301322 A	24-09-1998
			PL 321777 A	22-12-1997
WO 9517357	A	29-06-1995	US 5413972 A	09-05-1995
			DE 69407624 D	05-02-1998
			DE 69407624 T	09-04-1998
			EP 0735988 A	09-10-1996
			JP 9506852 T	08-07-1997
WO 8605811	A	09-10-1986	US 4861714 A	29-08-1989
			AT 98699 T	15-01-1994
			AU 5669486 A	23-10-1986
			DE 3689400 D	27-01-1994
			DE 3689400 T	07-04-1994
			EP 0217917 A	15-04-1987
			JP 62502936 T	26-11-1987
			CA 1288370 A	03-09-1991
			US 4997753 A	05-03-1991
			US 4863856 A	05-09-1989
			CA 1275955 A	06-11-1990
			US 5100783 A	31-03-1992
US 4915884	A	10-04-1990	FR 2612085 A	16-09-1988
			AT 64109 T	15-06-1991
			EP 0287136 A	19-10-1988
			JP 63302994 A	09-12-1988
US 4576718	A	18-03-1986	DE 3402697 A	01-08-1985
			AT 25959 T	15-04-1987
			CA 1249674 A	31-01-1989
			DK 37085 A	27-07-1985
			EP 0150747 A	07-08-1985
			FI 850318 A,B,	27-07-1985
			JP 60172399 A	05-09-1985